

# MATERIAL'S FEATURES

## Mechanical properties

Flexural elastic modulus	EN 15534-1:2014	37,4 Mpa
Impact resistance	ISO80-2000/Adm:2013	NO CRACK
Coefficient of linear thermal expansion longitudinal (from -10 °C to 45 °C)	EN 15534-1:2014	34,2 x10 <sup>-6</sup> K <sup>-1</sup>
Slip resistance	DIN EN 16165:2021	R10

## Reaction to fire

Reaction to fire	EN 13501 - 1:2007 + A1:2009	Cfl - S1
------------------	-----------------------------	----------

The values shown are indicative and not binding. Test reports available upon request.  
The natural aging of the material and temperature variations may cause deviations from the values indicated above.  
The product is protected by a warranty in line with legal requirements: for more information see the SPECS on [www.woodngreenwood.com](http://www.woodngreenwood.com)